

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-279979

(43)Date of publication of application : 20.10.1998

(51)Int.Cl.

C10M169/04
// (C10M169/04
C10M101:02
C10M105:02
C10M105:08
C10M105:76
C10M135:06
C10M135:10
C10M135:20
C10M139:00)
C10N 20:02
C10N 30:16
C10N 40:24

(21)Application number : 09-086303

(71)Applicant : IDEMITSU KOSAN CO LTD

(22)Date of filing : 04.04.1997

(72)Inventor : OKADA TAHEI

(54) RUST PREVENTING AND STAMPING OIL COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain the subject composition excellent in lubrication, rust-prevention and degreasing and capable of being coated without trouble by a current coating line for a rust-preventing oil by formulating a rust-preventing agent, an over based Ca sulfonate, a sulfur-based extreme-pressure agent and potassium borate with a lubricant base oil.

SOLUTION: This rust preventing and stamping oil composition is obtained by formulating (A) a rust-preventing agent (preferably an oxidized wax derivative and a metal sulfonate), (B) an over based Ca sulfonate (e.g. Ca salt of an alkylsulfonic acid), (C) a sulfur-based extreme-pressure agent (preferably an oil and fat sulfide) and (D) a potassium borate dispersion with a lubricant base oil (preferably the one having 2-40 mm²/s kinetic viscosity at 40° C). Further, the composition preferably contains 2-10 wt.% component A, 0.6-2.2 wt.% component B in terms of Ca part, (C) 0.3-2 wt.% component C in terms of sulfur part, and 0.2-0.7 wt.% component D in terms of boron part based on the whole amount of the composition. The objective composition preferably has 2-30 mm²/s kinetic viscosity at 40° C.

LEGAL STATUS

[Date of request for examination]

01.04.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision]